



| Product | FILLER | VOLUME SENSITIVITY Ohm-cm | MIX RATIO RESIN/CATALYST BY WEIGHT | SPECIFIC GRAVITY Gm/cc | OPEN TIME RT 25gm mass | Max Use Temp. °C | Cure Schedule |
|----------------|-----------------------|---------------------------|------------------------------------|------------------------|--------------------------------|------------------|---|
| E10-101 | Pure Silver | <.0003 | 100/5 | 2.8 | 1 Hour | 170 | 24 hrs @RT or 45 min @50° C 15 min @100° C |
| E10-102 | Nickel | 0.038 | N/A | 2.5 | 4 mth. @RT or 9 months refrig. | 325 | 1 hr @ ° 150 C |
| E10-104 | Pure Silver | 0.0001 | One Component | 2.8 | 4 mth. @RT or 9 months refrig. | 325 | 2 hrs @125° C 1 hr @150° C ½ hr @175° C |
| E10-106 | Silver Coated ceramic | 0.0015 | 100/5 | 2.6 | 1 hour | 170 | 8 hours @ RT |
| E10-108 | Pure Silver | 0.0001 | Equal parts | 2.85 | 2 hours | 115 | 16 hrs. @ RT or 2 hrs. @60° C |
| E10-110 | Pure Silver | 0.0001 | Equal parts | 2.85 | 4 Days | 325 | 1 hour @150° C |

