

TECHNICAL PRODUCT BULLETIN

GENERAL DESCRIPTION

E10-107 is a single component, heat curing, conductive epoxy polymer that was designed for ease in handling. This high performance conductive polymer cures quickly at elevated temperatures making it ideally suited for rapid Processing and assembly.

E10-107 offers excellent mechanical, electrical, and physical properties at continuous operating Temperatures up To 175°C. This versatile silver conductive adhesive can be used for chip bonding in Micro and electronic hybrid circuit Fabrication. This unique conductive polymer also exhibits outstanding adhesion to a wide variety of substrates with good hot strength at intermittent temperatures up to 325°C.

E10-107 has also been used in microwave applications for EMI and FRI shielding, for assembly and repair of circuit boards and Electronic component manufacturing.

STORAGE AND HANDLING

Since settling may occur in storage, remix each container prior to use. Refrigeration storage is recommended to minimize filler settling and to maintain viscosity and Electrical conductivity. If refrigeration storage is used, to avoid condensation, allow to stabilize to room Temperature before opening and removing material. OSHA Form 20 Material Safety Data Bulletins are available on request.

AVAILABILITY and PACKAGING

ALFA E10-107 is available for immediate delivery from stock in:

- Syringes: 2.5, 5, 10 and 20-gram sizes



- Jar Kit: 0.5 Lb., 1.0 Lb., 2.0 Lb.



**Custom sizes are available upon request*

32 Mechanic Avenue Unit 99 • Woonsocket RI 02895 • Tel. 401-765-0503 • Fax 401-765-0508 •
www.alfaadhesives.com • E-mail: info@ alfaadhesives.com

SPECIFICATIONS

HANDLING CHARACTERISTICS:

Base:	Epoxy
Solvent:	None
Carbon Additives:	None
Copper Additives:	None
Mixed Viscosity at 25°C, cps:	Soft Paste
Color, Filler:	Silver
Cure Schedule:	2 Hrs. at 125°C 1 Hr. at 150 °C ½ Hr. at 175°C
Shelf Life:	4 months – Room Temp 9 months – Refrigerate
Hardness Shore-D:	88

THERMAL CHARACTERISTICS

Thermal Conductivity w/m·k:	2.88-3.15
Operating Temp. Range, °C:	-55 to +175
Intermit. To:	32

ELECTRICAL CHARACTERISTICS

Volume Resistivity, ohm · cm:	0.0007
-------------------------------	--------

**THIS PRODUCT IS FOR INDUSTRIAL USE ONLY,
KEEP OUT OF REACH OF CHILDREN.**

Read and understand SDS before use. Liquid uncured epoxy material may cause skin sensitization or other allergic responses. Prevent all contact with skin or eyes. If contact occurs, flush immediately with plenty of water and get immediate medical attention